



## *Analysis of VOC in Polyester*

### **Analysis Condition**

**Column:** HP-5(25m x 0.32mm x 0.53um)

**Detector:** FID

**Inj. temp.:** 230°C

**Jet. temp. :** 250°C

**Column Flow:** 3.1ml/min

**Injection Volume:**0.5ml

**Oven temp. (Programming):** 50°C (2min) → 5°C/min → 150°C (5min)

